

## CASEA Södänit 400 Thermal Anhydrite Calcium Sulphate Floor Screed Binder

Södänit 400 Anhydrite Binder is a specially formulated thermal calcium sulphate binder suitable for the production of top-quality self levelling (flowing) floor screeds, simply by blending with a suitable sand and water on site or ready-mix plant. Södänit 400 Anhydrite Binder complies with EN 13454-1: 2004 and is CE marked.

- Pumpable – High Flowability
- Early Trafficking
- Very Low Shrinkage
- Reduced Drying Times
- CE Marked
- EN 13454-1: 2004

### Field Of Application

Södänit 400 Screed is suitable for floors in homes, offices, public buildings and places exposed to similar loads. Södänit 400 Screed may be applied as a levelling screed directly onto a load bearing floor, unbonded on a separating barrier (polythene), as a floating floor and is particularly suited in conjunction with underfloor heating or cavity floors. Södänit 400 Screed should be covered with a floor finish such as tiles, linoleum, parquet, cork or carpet. If a cement based adhesive or smoothing compound is required the surface of the screed must first be sealed, using an appropriate acrylic primer/sealer.

### Working Instructions

Light ventilation in the work area is necessary, but windows and openings must be closed sufficiently to avoid draughts, during and after application. Indoor and floor temperature should exceed +10°C during and after application and for one week after that.

### Substrate

Södänit 400 Screed is designed for use as a bonded thick levelling screed on concrete, as a floating screed over thermal or acoustic insulation, or as an unbonded screed on top of a plastic membrane.

### Preparation and Priming

The substrate should be clean, dry, free of dust, grease and other impurities that might prevent adhesion. If it is a large area the surface should be treated by mechanical preparation by grinding or shot blasting. For bonded screeds, the substrate must be dry and should be primed with a suitable primer. If Södänit 400 Screed is to be applied on plastic sheeting or as a floating floor, a gap of minimum 8mm should be formed around the perimeter (walls, columns, etc.).

### Mix Design

Sand should be of an approved quality and grading. Trials should always be carried out to optimize the mix design before work commences. The proportion of binder required is 540 – 600kg/m<sup>3</sup>. Sufficient sand is required to produce 1m<sup>3</sup> of screed, with sufficient water added to produce a flow spread diameter of 220-260mm. A typical starting point mix design is 600kg Binder, 1200kg sand (dry weight) and 330L water per m<sup>3</sup>. All materials should be adequately mixed to ensure full dispersion of materials without lumps.

### Application

Pumping is carried out in sections so that a wet edge is maintained. A wide steel tampering bar is used to assist the levelling process. When applied bonded the minimum thickness of Södänit 400 Screed should be 20mm, over underfloor heating this should be a minimum of 25mm over the pipes (35mm over insulation board).

### Storage

6 months under dry, protected conditions.

### Disposal Considerations

13.1 Waste treatment methods: Recommendation: Must not be disposed together with household garbage. Do not allow product to reach sewage system. Uncleaned packaging: Recommendation: Disposal must be made according to official regulations. Recommended cleansing agents: Water, if necessary together with cleansing agents.

### Safety

Caution: Contains Cement, portland, chemicals. See CASEA Health and Safety Data Sheet for further detailed information. Classification according to Regulation (EC) No 1272/2008: **GHS05**. Signal word: **Danger**. All standard precautions for the handling of construction materials/chemicals must be taken.

## Safety

### Hazard Statements

**H318** Causes serious eye damage.

### Precautionary Statements


**P102** Keep out of reach of children.

**P280** Wear eye protection / face protection.  
**P305+P351+P338** IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

**P310** Immediately call a POISON CENTER or doctor.

## Technical Information

Screed Specification EN 13813: 2002	
Maximum Thickness	90mm
Minimum Thickness	Bonded: 20mm Unbonded: 30mm Domestic: 35mm Commercial: 40mm Over Underfloor heating Pipes: 25mm (BS 8204-7)
Use (External Use)	No
Use (Internal Use)	Yes
Compressive Strength (28 days)	> 25 N/mm <sup>2</sup> > 30 N/mm <sup>2</sup>
Flexural Strength (28 days)	> 5 N/mm <sup>2</sup> > 7 N/mm <sup>2</sup>
Tensile Adhesion	> 1.5 N/mm <sup>2</sup>
Flow Rate	220 – 260 mm (slump flow - Hägermann cone)
Light foot traffic	10 – 12 hours
Hardening Time	Final Covering: 2 – 6 weeks dependent on thickness and drying conditions
Pot life (open time as mortar)	Maximum 40 minutes depending on ambient conditions.
Reaction To Fire	A1 Non-Combustible
Packaging	big bags and bulk

	<p>CASEA GmbH            Pontelstraße 3            99755 Ellrich            Germany</p>
	<p>06            04 16911 202            0432-BPR-220004379/01            EN 13454 -1: 2004            Calcium Sulphate binder CAB-40            For use internally in buildings</p>
Reaction to fire	A1
pH value	≥ 7
Strength Class	40
Calcium sulphate content	≥ 50 %
Shrinkage and swelling	≤ 0.2 mm/m

\*NPD = No Performance Determined

**CASEA**  
 WORKING FOR THE FUTURE



Smet Building Products Limited  
 93A Belfast Rd | Newry | Co. Down | BT34 1QH  
 T: +44 (0)28 3026 6833 F: +44 (0)28 3026 7619  
 E: info@smetbuildingproducts.com