




Sopro HPS 673

Bonding primer



Special light-grey, polymer dispersion-based, silica sand-modified, solvent-free primer, applied as bonding layer to impervious, smooth and non-absorbent substrates prior to surface filler application or tile laying.

Particularly suitable for laying on existing ceramic coverings. Also used as bonding primer on timber, mastic asphalt or magnesium oxychloride (magnesite) screeds and existing firmly adhering adhesive residue, lacquers/varnishes and PVC coverings.

- Ready-to-use and quick-drying
- Ideal for renovation and refurbishment
- High coverage
- Suitable for floor heating systems
- Approved for shipbuilding
- For walls and floors
- Solvent-free
- EMICODE system of GEV (German Association for Control of Emissions in Products for Flooring Installation): EC1^{PLUS} ("very-low-emission-plus") rating
- DGNB (German Sustainable Building Council): Top quality level 4, Line 8¹⁾
- For indoor and outdoor use

Use

For preparation of dense, smooth, closed-pore substrates to guarantee adhesion of surface fillers and tile adhesives. Sopro HPS 673 bonding primer also prevents unwanted chemical reactions between old, organic PVC, carpet, parquet or adhesive residue and hydraulically setting surface fillers and adhesives.

When applied as pretreatment to timber materials, Sopro HPS 673 prevents swelling of substrate. Application of Sopro HPS 673 provides surfaces with good key. Not suitable for underwater applications.

Suitable substrates

Smooth and non-absorbent substrates, e.g. existing ceramic tile, terrazzo, natural and cast stone coverings; mastic asphalt screeds without sand blinding, asphalt tiles, magnesium oxychloride (magnesite) screeds, non-absorbent concrete; timber substrates, e.g. particleboard and scuff-sanded parquet. Existing, firmly adhering uPVC and linoleum flooring, concrete sealers and screed coatings, adhesive residue from PVC flooring, carpeting or parquet.

Colour

Light grey

Drying time

1–2 hours

Application temperature

From +5 °C

Coverage

Approx. 150 g/m² depending on substrate

Shelf life

Approx. 12 months in original unopened containers; protect from frost

Packaging

10 kg bucket, 5 kg bucket, 3 kg bucket, 1 kg pot (Nr 10 in box)

¹⁾ Based on DGNB (German Sustainable Building Council) criterion "ENV1.2 Local Environmental Impact" (2015 version).

Substrate preparation

Substrate shall be solid, strong, rigid, permanently dry, clean and free from dirt, oil, wax, dust and loose particles.
All relevant standards, guidelines and recommendations shall apply; workmanship shall comply with good practice.

Application

Stir prior to use and apply in uniform, thin coat using brush, roller or smoother. Apply material moderately so as to avoid puddling. Work may resume immediately after priming coat has fully dried through. Sopro HPS 673 bonding primer shall be applied in undiluted form.
Note: Not suitable for underwater applications!

Specified times

Apply for normal temperature range of +23 °C and 50 % relative humidity; higher temperatures shorten and lower temperatures lengthen these times.

Tools/tool cleaning

Lambswool roller, foam roller, smoother, brush; wash tools with water immediately after use.

Test certificates

BG Verkehr (institution for statutory accident insurance and prevention for transport and traffic):

- Approval for shipbuilding in Sopro System 2.1 (wall), MED approval no. 118.222, USCG approval no. 164.112/EC0736/118.222. Wet-applied quantity Sopro HPS 673: max. 330 g/m². Other components in Sopro System 2.1: Sopro FKM XL 444 multi-purpose eXtraLight flexible tile adhesive, fully vitrified stoneware tile (thickness 5 mm), Sopro FEP epoxy tile grout. Joints ≤ 4 mm.
- Approval for shipbuilding in Sopro System 2.5 (wall), MED approval no. 118.405, approval no. 164.112/EC0736/118.405. Wet-applied quantity Sopro HPS 673: max. 200 g/m². Other components in Sopro System 2.5: Sopro FKM XL 444 multi-purpose eXtraLight flexible tile adhesive, fully vitrified stoneware tile (thickness 8 mm), Sopro FEP plus epoxy tile grout. Joints ≤ 6 mm.
- Approval for shipbuilding in Sopro System 3.1 (floor), MED approval no. 124.096, USCG approval no. 164.117/EC0736/124.096. Wet-applied quantity Sopro HPS 673: max. 330 g/m². Other components in Sopro System 3.1: Sopro FKM XL 444 multi-purpose eXtraLight flexible tile adhesive, fully vitrified stoneware tile (thickness 5 mm), Sopro FEP epoxy tile grout. Joints ≤ 4 mm.
- Approval for shipbuilding in Sopro System 3.7 (floor), MED approval no. 124.126, USCG approval no. 164.117/EC0736/124.126. Wet-applied quantity Sopro HPS 673: max. 280 g/m². Other components in Sopro System 3.7: Sopro FKM XL 444 multi-purpose eXtraLight flexible tile adhesive, fully vitrified stoneware tile (thickness 8 mm), Sopro FEP plus. Joints ≤ 6 mm.
- Approval for shipbuilding in Sopro System 3.9 (floor) MED approval no. 124.125, USCG approval no. 164.117/EC0736/124.125. Wet-applied quantity Sopro HPS 673: max. 280 g/m². Other components in Sopro System 3.9: Sopro FKM XL 444 multi-purpose eXtraLight flexible tile adhesive, Sopro FAS 551 fibre-reinforced self-levelling filler, fully vitrified stoneware tile (thickness 8 mm), Sopro TF- high-strength tile grout. Joints ≤ 6 mm.

Please observe technical product information for relevant system components.

Licence

EMICODE system of GEV (German Association for Control of Emissions in Products for Flooring Installation): EC1^{PLUS} ("very-low-emission-plus") rating

Safety precautions

Not classified as dangerous under Regulation (EC) No 1272/2008 (CLP).

All standard precautions for the handling of construction materials/chemicals shall be taken.

EUH208 Contains 1,2-benzisothiazol-3(2H)-one. May produce an allergic reaction. **EUH208** Contains a mixture of: 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one in proportions 3:1. May produce an allergic reaction. Avoid contact with skin. **EUH210** Safety data sheet available on request.

Precautionary statements: P102 Keep out of reach of children. **P332+P313** If skin irritation occurs: Get medical advice/attention.

German Water Hazard Class (WGK): WGK 1: slightly hazardous to water (self-assessment in accordance with VwVwS – German Administrative Regulations on the Classification of Substances Hazardous to Waters into Water Hazard Classes – of 17.05.1999)

GHS/GHS (German hazardous substances classification): D1

Disposal

Waste treatment methods

Recover if possible. In so doing, comply with the local and national regulations currently in force.

91/156/EEC, 91/689/EEC, 94/62/EC and subsequent amendments.

Disposal of hardened product (EC waste code) : 08 04 10

Disposal of not hardened product (EC waste code) : 08 04 14

The suggested European waste code is just based on the composition of the product.

According to the specific process or application field a different waste code may be necessary

bringing european innovation

smet


FOR MORE INFORMATION CONTACT: Smet Building Products Ltd

98A Belfast Road | Newry | BT34 1QH | Northern Ireland

T: +44 (0)28 3026 6633 F: +353 (0) 1697 8586

E: info@smetbuildingproducts.com

smetbuildingproducts.com or smet.ie



Marketplace+

The information, and, in particular, the recommendations relating to the application and end-use of SMET distributed products, are given in good faith based on SMET's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with the manufacturer's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. The manufacturer reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.