



Sopro Repadur 50

PCC concrete repair mortar



Fibre-reinforced, cementitious mortar for concrete replacement, reprofiling and large-scale coating of concrete substrates, for use in concrete repair works complying with ZTV-ING (Special technical contract terms and guidelines for engineering structures) and concrete repair guidelines issued by DafStb (German Committee for Reinforced Concrete).

- One-component
- Mineral-based
- Fibre-reinforced
- Coat thickness: 10–50 mm

PCC system

Sopro Repadur 50 forms part of **Sopro Repadur system**, a PCC concrete replacement system suitable for PCC I and PCC II applications to ZTV-ING (Special technical contract terms and guidelines for engineering structures) and for duty classes M2/PCC I and M2/PCC II to SIB (Protection and repair of concrete elements) guidelines issued by DafStb (German Committee for Reinforced Concrete). Sopro Repadur system comprises:

Corrosion protection: Sopro Repadur KS
Bonding layer: Sopro Repadur MH
Concrete replacement: Sopro Repadur 50
Fine filler: Sopro Repadur 5

Use

Concrete replacement/repair mortar for PCC I and PCC II applications to ZTV-ING and for duty classes M2/PCC I and M2/PCC II to concrete repair guidelines issued by DafStb. For reprofiling of damaged concrete substrates, repair of concrete elements subject to dynamic loads and large-scale coating of concrete surfaces.

Mixing ratio

2.6 ltr water : 25 kg Sopro Repadur 50;
 11 parts water : 100 parts Sopro Repadur 50 powder

Working life

Approx. 90 minutes at +5 °C; approx. 60 minutes at +23 °C; approx. 30 minutes at +30 °C

Colour

Grey

Maximum aggregate diameter

3 mm

Consistency

Soft and plastic

Apparent density of fresh mortar

Approx. 2.2 kg/dm³

Shrinkage

< 0.90 mm/m

Compressive strength

Approx. 30 N/mm² after 1 day; approx. 50 N/mm² after 7 days; approx. 60 N/mm² after 28 days

Flexural tensile strength

Approx. 6 N/mm² after 1 day; approx. 8 N/mm² after 7 days; approx. 9 N/mm² after 28 days

Tensile adhesion strength

> 2.0 N/mm² to concrete after 28 days

Application temperature

From +5 °C to max. +30 °C (substrate, air, material)

Coverage

Approx. 2.0 kg/m² per mm coat thickness

Shelf life

Approx. 12 months, subject to storage on pallet in dry conditions in original unopened containers

Packaging

25 kg bag, 5 kg bag

Properties

Sopro Repadur 50 is a premixed dry mortar comprising high-grade cement, specially graded aggregate, special additives and synthetic fibres.

It is mixed with water to produce a very smooth, easily workable and sag-resistant fresh mortar.

Sopro Repadur 50 meets requirements of TL/TP BE-PCC (Technical delivery conditions/technical test conditions for PCC concrete repair systems).

Sopro Repadur 50 can be applied in coat thicknesses of 10–50 mm.

Substrate preparation

Remove loose or insufficiently strong parts of substrate to expose rough, mineral, strong core concrete. Edges of damaged areas/surface cavities shall be cut away at 30°–60° angle and surface left rough. Roughen entire concrete substrate using suitable surface preparation method (e.g. blast cleaning with health-hazard-free abrasive or high-pressure water jetting) to remove dirt/soiling, laitance, paint/coating residue and other adhesion-impairing substances.

Prepared substrate shall exhibit a mean pull-off strength of min. 1.5 N/mm². Please consult Sopro Technical Service team regarding applicability of Sopro Repadur 50 where this value is not attainable.

Use light hacking tool to remove concrete and expose corroded reinforcement. Blast clean with health-hazard-free abrasive to preparation grade SA 2½ to DIN EN ISO 12944-4.

Immediately after treatment, apply two full-cover coats of Sopro Repadur KS PCC corrosion-inhibiting mortar to reinforcing bars. Prior to treatment with system bonding layer (Sopro Repadur MH), prepared concrete surfaces shall be pre-wetted to saturation and then allowed to dry to slightly damp, matt appearance at time of bonding layer application.

Application

Mix 25 kg (1 bag) Sopro Repadur 50 with approx. 2.6 ltr (min. 2.5 ltr) water (105 ml water per kg powder). First pour approx. 2/3 of mixing water into clean container. While stirring, gradually add dry mortar and remaining mixing water. Thoroughly mix together constituents for approx. 3 minutes to a homogeneous, lump-free consistency. Briefly restir fresh material after approx. 2 minutes maturing time. A slow-speed mechanical stirrer (approx. 400 rpm) with suitable attachment may be used to mix quantities up to 25 kg. Use forced-action mixer to prepare larger quantities of fresh mortar. Fresh mortar is workable for approx. 60 minutes (at +23°C and 50% relative humidity).

Apply Sopro Repadur 50 wet-on-wet to substrate pretreated with full-cover Sopro Repadur MH PCC mortar bonding layer. Work material into bonding layer, thoroughly compact and strike off flush with adjoining surfaces. After fresh mortar has firmed up (initial set), surface of Sopro Repadur 50 may be worked over as required using wooden or plastics float. Coat thicknesses up to 20 mm can be applied in single operation.

For greater thicknesses to vertical or overhead surfaces, application of material in several coats is recommended. In such cases, following coat may be applied as soon as preceding coat has firmed up.

Where material of preceding coat has already surface-dried, pretreatment with Sopro Repadur MH PCC mortar bonding layer is required prior to application of following coat.

Suitable measures shall be taken to protect placed mortar against frost and premature moisture loss for a period of 5 days.

Protection against premature water loss after application is essential to prevent cracking. Use of evaporation-inhibiting curing compounds – as an alternative to standard curing methods such as dampening or covering with sheet – is only possible where no subsequent coatings are to be applied.

Specified times

Apply for normal temperature range of +23°C and 50% relative humidity; higher temperatures shorten and lower temperatures lengthen these times.

Tools/tool cleaning

Clean tools with water immediately after use; mechanical cleaning required when set

Safety precautions

Labelling in accordance with Regulation (EC) No 1272/2008 (CLP)

GHS05, GHS07

Signal word: Danger

Contains Portland cement. Exhibits strong alkaline reaction upon contact with moisture/water; protection required for skin and eyes. All standard precautions for the handling of construction materials/chemicals shall be taken.

Hazard statements: H315 Causes skin irritation. H318 Causes serious eye damage. H335 May cause respiratory irritation.

Precautionary statements: P102 Keep out of reach of children. P261 Avoid breathing dust. P280 Wear protective gloves/protective clothing/eye protection/face protection. P302+P352 IF ON SKIN: Wash with plenty of water and soap. P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. P310 Immediately call a POISON CENTER or doctor. P332+P313 If skin irritation occurs: Get medical advice/attention.

GISCODE (German hazardous substances classification): ZP 1 - Low-chromate to Regulation (EC) No 1907/2006, Annex XVII

Disposal

Waste treatment methods

Recover if possible. In so doing, comply with the local and national regulations currently in force.

91/156/EEC, 91/689/EEC, 94/62/EC and subsequent amendments.



Disposal of hardened product (EC waste code) : 17 01 01

Disposal of not hardened product (EC waste code) : 17 01 01

The suggested European waste code is just based on the composition of the product.

According to the specific process or application field a different waste code may be necessary.

CE marking

 1119 1508	 Sopro Bauchemie GmbH Biebricher Straße 74 - 65203 Wiesbaden (Germany) www.sopro.com
	14 CPR-DE3/0852.1.eng EN 1504-3:2005 Sopro Repadur 50 (852) PCC hydraulic mortar (EN 1504-3:2005 R4 PCC) for structural and non structural repair of concrete in buildings and civil engineering works
Reaction to fire	Class E
Compressive strength	Class R4
Chloride ion content	≤ 0,05 %
Adhesive Bond	≥ 2,0 MPa
Restrained shrinkage/expansion	NPD
Carbonation Resistance	bestanden
Elastic Modulus	NPD
Thermal Compatibility	
- Freeze-thaw	≥ 2,0 MPa
Skid resistance	NPD
Coefficient of thermal expansion	NPD
Capillary Absorption	≤ 0,5 kg*m ⁻² *h ^{-0,5}
Dangerous substances	see SDS

bringing european innovation

smet


FOR MORE INFORMATION CONTACT: **Smet Building Products Ltd**

93A Belfast Road | Newry | BT34 1QH | Northern Ireland

T: 44 (0)28 3026 6833 F01: 353 (0) 1687 8586

E: info@smet.buildingproducts.com

smetbuildingproducts.com or smet.ie



The information, and, in particular, the recommendations relating to the application and end-use of SMET distributed products, are given in good faith based on SMET's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with the manufacturer's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. The manufacturer reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.