

## Streetscape<sup>®</sup> Rapid-Set Jointing Mortar

A superior quality rapid-set jointing mortar, manufactured under an ISO 9001 quality controlled environment; using dried sands, lime, cement and additives specially designed to meet or exceed the requirements of BS 7533 parts 7 & 12. The product is ideal for jointing of natural stone setts and cobbles, flags, concrete and clay pavers in a rigid, bonded construction.

- Complies with BS 7533 parts 7 & 12
- 5 - 50mm joint widths
- Up to 200mm joint depths
- Shrinkage compensated
- Light foot traffic within 1 hour
- Frost Resistant
- Consistently high quality
- Long term durability

### Working Instructions

Rapid-Set Jointing Mortar should only be used in bonded rigid constructions. The product should not be used in temperatures below 3° C in a falling temperature or below 1° C on a rising thermometer. The surface of the substrate should not be frozen or >30° C before bedding commences. Movement joints will be required in rigid/bonded constructions and should be designed and marked by the design team.

### Substrate

The substrate, including sub-base and road base should meet the requirements of the relevant part of BS7533 dependent on type of use.

### Preparation

All paving stones should be clean and thoroughly sound, free from oils, grease, dust, loose particles or any other contaminants which may interfere with adhesion. Paving stones should be wet before jointing starts in order to prevent staining.

### Mixing

Add the contents of the 25kg bag to approximately 4.25 litres of clean water and mix for 3 – 4 minutes, using a suitable bell mixer. Add the product gradually to create a lump-free flowing slurry. DO NOT remix or add additional water to the mix at a later stage. Only mix enough material which can be placed within 10 mins.



### Application

Pour the jointing mortar onto the pre-wetted pavement and chase into the joints using a squeegee. Ensure joints are full to the surface allowing for settlement. The surface of the pavement must be kept moist during the curing process. Sweep off any excess material with the squeegee when joints are full. When the joint has sufficiently hardened, to prevent washout, the cleaning process can begin. This can be as soon as 15 minutes depending on ambient temperature. Timing and experience is crucial to ensure no staining occurs. A constant flow of water in conjunction with a diagonal sweeping by squeegee action will remove the excess mortar from the paving surface. Depending on the stone surface, further cleaning by pressure washer may be required. For best results a specifically designed belt cleaner can also be used. Inspect the paving surface to ensure all excess mortar is removed. N.B. full training will be provided on site by SMET personnel in order to achieve best results using this product.

**PRECAUTIONS:** Wash all tools and equipment frequently to avoid staining. Ensure correct procedures are followed to avoid product staining. Placement time and ambient temperatures, at the time of placement, are factors to be considered to ensure no staining occurs. Only mix enough material which can be placed in 10 mins. Once the material has stiffened (initial set), clean the paving units and their surrounding area thoroughly.

## Storage

Both bulk bags and packed products must be stored clear of the ground in cool, dry conditions and protected from wind, rain and external physical damage. Packed products must be stored in unopened, original bags.

## Disposal Considerations

Wearing appropriate personal protective equipment, place spilled wet product in a suitable container. The product will set as a hard material.

## Safety

Caution: This product contains Portland Cement, Calcium Aluminate Cement, Limestone aggregates and chemical Additives. See Kilsaran Health and Safety Data Sheet for further detailed information. Classification according to Regulation (EC) No 1272/2008: **GHS05 corrosion**. Signal word: **Danger**. All standard precautions for the handling of construction materials/chemicals must be taken.

## Hazard Statements

H315: Causes skin irritation.  
H317: May cause an allergic skin reaction.  
H318: Causes serious eye damage.  
H335: May cause respiratory irritation.

## Precautionary Statements

P102: Do not handle until all safety precautions have been read and understood  
P260: Do not breathe dust/fume/gas/mist/vapours/spray  
P305+P361+P338: If in eyes: rinse cautiously with water for several minutes  
P302+P352: If on skin: wash with plenty of soap and water  
P302+P350: If on skin: Gently wash with plenty of soap and water  
P280: Wear protective gloves/protective clothing/eye protection/face protection

## Technical Information

<b>Streetscape®: Rapid-Set Jointing Mortar</b>	
Compressive Strength (28 days) (BS EN 1015-11)	> 53 N/mm <sup>2</sup>
Adhesion Strength (BS EN 1015-12)	> 1.5 N/mm <sup>2</sup>
Flexural Strength (28 days) (BS EN 1015-11)	> 9.0 N/mm <sup>2</sup>
Modulus Of Elasticity (DIN 18555-6)	20,000 N/mm <sup>2</sup>
Density (BS EN 1015-11)	2060 kg/m <sup>3</sup>
Shrinkage (BS EN 445)	< 0.10%
Use (External Use)	Yes
Use (Internal Use)	Yes
Yield per 25kg (dry material)	approx. 13.5 litres
Initial Set	15 min
Final Set	60 min
Pot life	Maximum 10 minutes (depending on ambient conditions)
Colour	Standard Grey (other colours can be specially ordered)
Packaging	25kg Bags




Smet Building Products Limited  
93A Belfast Rd | Newry | Co. Down | BT34 1QH  
T: +44 (0)28 3026 6833 F: +44 (0)28 3026 7619  
E: info@smetbuildingproducts.com