

Streetscape® Rapid-Set Jointing Mortar

A superior quality rapid-set jointing mortar, manufactured under an ISO 9001 quality controlled environment; using dried sands, lime, cement and additives specially designed to meet or exceed the requirements of BS 7533 parts 7 & 12. The product is ideal for jointing of natural stone setts and cobbles, flags, concrete and clay pavers in a rigid, bonded construction.

- Complies with BS 7533 parts 7 & 12
- 5 - 50mm joint widths
- Up to 200mm joint depths
- Shrinkage compensated
- Light foot traffic within 1 hour
- Frost Resistant
- Consistently high quality
- Long term durability

Working Instructions

Rapid-Set Jointing Mortar should only be used in bonded rigid constructions. The product should not be used in temperatures below 3°C in a falling temperature or below 1°C on a rising thermometer. The surface of the substrate should not be frozen or >30°C before bedding commences. Movement joints will be required in rigid/bonded constructions and should be designed and marked by the design team.

Substrate

The substrate, including sub-base and road base should meet the requirements of the relevant part of BS7533 dependent on type of use.

Preparation

All paving stones should be clean and thoroughly sound, free from oils, grease, dust, loose particles or any other contaminants which may interfere with adhesion. Paving stones should be wet before jointing starts in order to prevent staining.

Mixing

Add the contents of the 25kg bag to approximately 4.25 litres of clean water and mix for 3 – 4 minutes, using a suitable bell mixer. Add the product gradually to create a lump-free flowing slurry. DO NOT remix or add additional water to the mix at a later stage. Only mix enough material which can be placed within 10 mins.



Application

Pour the jointing mortar onto the pre-wetted pavement and chase into the joints using a squeegee. Ensure joints are full to the surface allowing for settlement. The surface of the pavement must be kept moist during the curing process. Sweep off any excess material with the squeegee when joints are full. When the joint has sufficiently hardened, to prevent washout, the cleaning process can begin. This can be as soon as 15 minutes depending on ambient temperature. Timing and experience is crucial to ensure no staining occurs. A constant flow of water in conjunction with a diagonal sweeping by squeegee action will remove the excess mortar from the paving surface. Depending on the stone surface, further cleaning by pressure washer may be required. For best results a specifically designed belt cleaner can also be used. Inspect the paving surface to ensure all excess mortar is removed. N.B. full training will be provided on site by SMET personnel in order to achieve best results using this product.

PRECAUTIONS: Wash all tools and equipment frequently to avoid staining. Ensure correct procedures are followed to avoid product staining. Placement time and ambient temperatures, at the time of placement, are factors to be considered to ensure no staining occurs. Only mix enough material which can be placed in 10 mins. Once the material has stiffened (initial set), clean the paving units and their surrounding area thoroughly.

Approximate Product Yield (10mm Joint)			
Paving Flag	25kg Yield (m ²)	Paving Block	25kg Yield (m ²)
400x400x40	7.1	100x100x60	2.4
400x400x50	5.8	100x100x80	1.8
400x400x60	4.8	200x100x60	1.7
450x450x40	8.1	200x100x80	1.3
450x450x50	6.4	200x200x60	1.3
450x450x60	5.4	200x200x80	1.0
600x300x50	5.8	240x160x60	2.5
600x300x60	4.8	240x160x80	1.9
600x600x50	8.6	200x300x60	2.9
600x600x60	7.1	200x300x80	2.2

The information, and, in particular, the recommendations relating to the application and end-use of SMET distributed products, are given in good faith based on SMET's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with the manufacturer's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. The manufacturer reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Streetscape® Rapid-Set Jointing Mortar

Storage

Both bulk bags and packed products must be stored clear of the ground in cool, dry conditions and protected from wind, rain and external physical damage. Packed products must be stored in unopened, original bags.

Disposal Considerations

Waste treatment methods: Alternative uses should be sought for any surplus mortar. Mortar waste should be disposed of in accordance with local authority guidance/regulations. Avoid entry of mortar waste into sewage or drainage systems or bodies of water, e.g. streams and rivers.

Safety

Classification according to Regulation (EC) No 1272/2008. Hazard pictograms: **GHS05** corrosion. Signal Word: **Danger**. Hazard-determining components of labelling: **Contains Portland Cement**. All standard precautions for the handling of construction materials/chemicals must be taken. Get medical advice / attention IF YOU FEEL UNWELL. See Kilsaran Health and Safety Data Sheet for further detailed information.

Hazard Statements

- H315: Causes skin irritation.
- H317: May cause an allergic skin reaction.
- H318: Causes serious eye damage.
- H335: May cause respiratory irritation.

Precautionary Statements

- P102: Keep out of reach of children.
- P202: Do not use until all safety precautions have been read and understood.
- P260: Do not breathe dust/fume/gas/mist/vapours/spray
- P262: Do not get in eyes, on skin or on clothing.
- P280: Wear protective gloves / protective clothing / eye protection / face protection.
- P305+P351+P338+P310: IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses if present and easy to do so. Continue rinsing. Get medical advice / attention.
- P302+P352+P333+P313: IF ON SKIN: Wash with plenty of soap and water. If skin irritation or rash occurs get medical
- P501 Disposal: Allow to harden and dispose of as mortar waste. advice / attention.
- P362: Take off contaminated clothing
- P363: Wash contaminated clothing before reuse
- P403+P233 Store in well-ventilated place. Keep container tightly closed.
- P405: Store locked up.

Technical Information

Streetscape®: Rapid-Set Jointing Mortar	
Compressive Strength (28 days) (BS EN 1015-11)	> 53 N/mm ²
Adhesion Strength (BS EN 1015-12)	> 1.5 N/mm ²
Flexural Strength (28 days) (BS EN 1015-11)	> 9.0 N/mm ²
Modulus Of Elasticity (DIN 18555-6)	20,000 N/mm ²
Density (BS EN 1015-11)	2060 kg/m ³
Shrinkage (BS EN 445)	< 0.10%
Use (External Use)	Yes
Use (Internal Use)	Yes
Yield per 25kg (dry material)	approx. 13 litres
Initial Set	15 min
Final Set	60 min
Pot life	Maximum 10 minutes (depending on ambient conditions)
Colour	Standard Grey (other colours can be specially ordered)
Packaging	25kg Bags

