

# PRODUCT DATA SHEET


Jan 2016

## FIBERGLASS MESH SGG22 UNIVERSAL

**Solid**  
Baustoffe

**Item number:** 1310-050 / 1311-050  
**Square dimension:** 10 x 10 mm  
**Width:** 100 cm  
**Colour:** 1310-050 white / 1311-050 blue

**Packaging unit:** RM/rolls      rolls/pallet  
Rolls                      50                      25



### TECHNICAL DATA:

**Material:**  
Warp: E-glass  
Shot: E-glass

**Thread density: (10 cm)**  
Warp: 10 turner strings  
Shot: 10 weft threads

**Treated fabric weight:** 145 g/m<sup>2</sup>  
**Loss of ignition:** 25 %  
**Characteristics:** alkali-resistant, obstructing yarn drifting

### Tensile strength per 5 cm:

STATE OF DELIVERY:	MEASURED VALUE:
Tensile strength warp (N/5 cm)	1945 N
Tensile strength shot (N/5 cm)	2210 N
28 DAYS STORAGE TO 5 % SODIUM HYDROXIDE:	
Tensile strength warp (N/5 cm)	1265 N
Tensile strength shot (N/5 cm)	1195 N

**Made in Europe**

The information, and, in particular, the recommendations relating to the application and end-use of SMET distributed products, are given in good faith based on SMET's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with the manufacturer's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. The manufacturer reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product

bringing european innovation



**smet**