




Sopro LZ 987

SMART® lightweight aggregate



Lightweight mineral aggregate made from expanded glass granulate for use in conjunction with Sopro Rapidur® B5 rapid-set screed binder to produce compression-resistant, rapid-set and early overcoatable lightweight levelling layers with thermal and sound insulation properties. Suitable for all coat thicknesses upwards of 20 mm in bonded construction. For filling pipe penetrations, large voids and sanitary service runs/assemblies. Ideal for refurbishment/renovation contracts. Can be laid to falls. Also suitable for use as loose fill.

- Mineral-based
- Ideal for refurbishment/renovation contracts
- Non-combustible
- Moisture-resistant and permanently dimensionally stable
- Offering thermal and sound insulation
- For levelling between pipes
- Pumpable

In conjunction with Sopro Rapidur® B5 rapid-set screed binder to produce compression-resistant, rapid-set and early overcoatable lightweight levelling layers with thermal and sound insulation properties. For levelling out large irregularities, filling pipe penetrations, service shafts, large voids and sanitary service runs/assemblies. As base for conventional screeds on separating layer or insulation. Can be laid to falls. Also suitable for use as loose fill.

25 kg (1 bag) Sopro Rapidur® B3 or Sopro Rapidur® B5 : 36 kg
or 220 ltr (4 bags) Sopro LZ 987; approx. 13–15 ltr water
12.5 kg (1/2 bag) Sopro Rapidur® B3 or Sopro Rapidur® B5 : 18 kg
or 110 ltr (2 bags) Sopro LZ 987; approx. 6.5–7.5 ltr water

Approx. 40–60 minutes (in conjunction with Rapidur® B3)
Approx. 2–3 hours (in conjunction with Rapidur® B5)

After approx. 4 hours with Sopro Rapidur® B3; after approx. 12 hours with Sopro Rapidur® B5.

≥ 20 mm for bonded construction; ≥ 35 mm on separating or on insulation layer;
≥ 20 mm pipe cover.

Approx. 1 N/mm²

0.075 W/m² K

Up to 10 dB*

4 – 6 mm

Sopro LZ 987: approx. 1.6 kg/m² or approx. 10 ltr/m² per cm coat thickness
Sopro Rapidur® B3 or Sopro Rapidur® B5: approx. 1.2 kg/m² per cm coat thickness

Approx. 320 kg/m³ (with Sopro Rapidur® B3 or Sopro Rapidur® B5)

A1 to DIN 4102

No size limit (min. tile thickness > 6 mm)

100 m²

A1, A3 and A3; max. area load 2.0 kN/m², max. point load 1.0 kN/m²
(in conjunction with Sopro VS 582 self-levelling filler > 10 mm coat thickness)

Bonded: From +5°C to +25°C (substrate, air, material)

Unbonded: All temperatures

* Test stand value to DIN EN ISO 140-8 serving as a general guide.
The performance of trial installations and measurements is therefore recommended, in each case, to establish the actual impact sound reduction index achievable on site.

Use

Mixing ratio

Working life

Overcoatable/loadable

Coat thicknesses

Compressive strength

Thermal conductivity

Impact sound reduction

Aggregate size

Coverage

Dry apparent density

Fire rating

Tile format


Max. bay size

Live loads to EN 1991

Application temperature

Construction heights and weights per unit area

Construction	mm	kg/m ²	
Sopro VS 582* and Sopro PG-X 1188	10	21,0	A
Sopro LZ 987 with Sopro Rapidur® B3/B5 (bonded)	20	6,6	B
Sopro SMART® system incl. Sopro VS 582 and Sopro PG-X 1188	30	27,6	C
	40	30,9	
	50	34,2	



* To achieve strong bond and interlock between self-levelling filler and Sopro SMART® light levelling layer, filler penetrates approx. 2 mm into top part of this layer. Allowance is made for this additional consumption.

Shelf life

Approx. 24 months, subject to storage on pallet in dry conditions in original unopened containers

Packaging

9 kg bag (approx. 55 ltr)

Substrate preparation

For bonded construction, substrate shall be strong, dimensionally stable and free from adhesion-impairing substances (e.g. dust, oil, wax, release agent, efflorescence, laitance, paint, lacquer and varnish residue, old flooring adhesive residue). For unbonded construction, substrate shall be strong. As a rule, installation of perimeter insulation strip is required to avoid sound transmission paths and for subsequent overcoating.

Construction types

Bonded construction with concrete or cement screed: In case of bonded construction with concrete or cement screed, material may be laid horizontally or to falls. Where necessary, mechanically roughen substrate, suction clean, pre-wet and prime with Sopro HS 448 bonding slurry with trass, Sopro HSF 748 flexible bonding slurry with trass or Sopro RS 648 vibration slurry. Place lightweight levelling mortar, comprising Sopro LZ 987 and Sopro Rapidur® B3 or Sopro Rapidur® B5, wet on wet. Minimum coat thickness:

20 mm

On separating layer: Lightweight levelling mortar, comprising Sopro LZ 987 and Sopro Rapidur® B3 or Sopro Rapidur® B5, may be applied to separating layers in a minimum coat thickness of 35 mm.

On insulation layer: Lightweight levelling mortar, comprising Sopro LZ 987 and Sopro Rapidur® B3 or Sopro Rapidur® B5, may be applied to thermal insulation board or sheet as well as impact-sound insulation mats or board in a minimum coat thickness of 35 mm. A PE sheet is recommended as an intermediate layer. Nominal mortar thickness of min. 35 mm is required on insulation layers subject to vertical live loads ≤ 2 kN/m², for insulation layer compressibility ≤ 5 mm. For divergent loads, specifications of DIN 18560 Part 2 shall apply.

On wood-board flooring: Lightweight levelling mortar, comprising Sopro LZ 987 and Sopro Rapidur® B3 or Sopro Rapidur® B5, may be applied directly to strong wood-board floors with sealed joints, subject to minimum coat thickness of 35 mm. Pretreat timber substrate with Sopro HPS 673 bonding primer. Then place lightweight levelling mortar.

Existing joints in wood-board floor shall be sealed in advance with Sopro DA 049 acrylic sealant.

Note: Make provision for prescribed waterproofing in damp spaces.

Application

All standard mixing and pumping equipment are suitable for use.

Mixing ratio:

25 kg (1 bag) Sopro Rapidur® B3 or Sopro Rapidur® B5 : 36 kg

or 220 ltr (4 bags) Sopro LZ 987; approx. 13–15 ltr water

12.5 kg (1/2 bag) Sopro Rapidur® B3 or Sopro Rapidur® B5 : 18 kg

or 110 ltr (2 bags) Sopro LZ 987; approx. 6.5–7.5 ltr water

Mix lightweight levelling mortar to earth-moist consistency. No other cements or screed admixtures shall be added. Laying procedure is same as for earth-moist screed. Mixing, placing and trowelling shall be performed in immediate succession. Only lay screed sections that may be completed within working life of mortar. Stiffened material shall not be rettempered by addition of water or mixing with fresh material to restore workability.

All standard mixing and pumping equipment are suitable for use.

Note: For mechanical pumping/delivery, binder content (Sopro Rapidur B3/B5) and amount of water added shall be increased by 50%.

Specified times

Apply for normal temperature range of +23°C and 50 % relative humidity; higher temperatures shorten and lower temperatures lengthen these times.

Safety precautions

Labelling of Sopro LZ 987: Exempt from labelling requirements under Regulation (EC) No 1272/2008 (CLP).

All standard precautions for the handling of construction materials/chemicals shall be taken.

Precautionary statements: P102 Keep out of reach of children. **P332+P313** If skin irritation occurs: Get medical advice/attention.

Disposal

13.1. Waste treatment methods

Recover if possible. In so doing, comply with the local and national regulations currently in force.

A waste code according to European waste catalogue (EWC) cannot be specified, due to dependence on the usage. Contact an authorized waste disposal service.

Do not dispose of waste into sewers.

Do not contaminate ponds, waterways or ditches with chemical or used container.

Send to an authorized waste disposal service.

Contaminated packaging:

Empty remaining content.

Dispose of as unused product.

Do not re-use empty containers.

bringing european innovation

smet

FOR MORE INFORMATION CONTACT: **Smet Building Products Ltd**

93A Belfast Road | Newry | BT34 1QH | Northern Ireland

T: +44 (0)28 3026 6833 ROI: +353 (0) 1697 8586

E: info@smetbuildingproducts.com

smetbuildingproducts.com or smet.ie



The information, and, in particular, the recommendations relating to the application and end-use of SMET distributed products, are given in good faith based on SMET's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with the manufacturer's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. The manufacturer reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.