

Special synthetic resin primer

SG 602



Special, solvent-free, one-component, synthetic resin primer for high- and variable-suction substrates. Dilutable with water to suit application. Specifically for calcium sulphate screeds when laying large-format fully vitrified stoneware units. Particularly suitable for subsequent application of mineral adhesives, surface fillers and waterproof membranes.

- For walls and floors, indoors
- Specifically for calcium sulphate and self-levelling calcium sulphate screeds when laying large-format fully vitrified stoneware units $\leq 1 \text{ m}^2$
- For cementitious substrates, may be diluted up to max. 1:3
- For cement and lime render, may be diluted up to max. 1:4
- In undiluted form also suitable for non-absorbent substrates
- Overcoatable: after 2-5 hours
- Acting as barrier coat
- Suitable for use in conjunction with floor heating
- Solvent-free
- GHS/GHS (German hazardous substances classification): D1
- DGNB: Top quality level 4, Line 8, based on DGNB (German Sustainable Building Council) criterion "ENV1.2 Local Environmental Impact" (2015 version).

Coverage: Approx. 50 – 150 g/m² depending on substrate suction. For calcium sulphate-based substrates, 100 – 150 g/m². Additional crosswise application is required in case of very high substrate suction.

Packaging		Packages	Pallet weight
Canister	5 kg	90	450 kg
Canister	10 kg	60	600 kg
Canister	20 kg	24	480 kg

Use	Sopro SG 602 primer reduces absorbency and evens out variable suction in substrate. It protects against moisture from bedding adhesive. It stabilizes friable surfaces and binds loose particles. Sopro SG 602 improves adhesion. It prevents bubbling where overcoated by surface fillers and waterproof membranes; premature water loss is prevented where thin-bed tile adhesives and waterproof membranes are subsequently applied. As primer on calcium sulphate screeds for normal and rapid-set Sopro thin-bed adhesives, for tile sizes $\leq 1 \text{ m}^2$.
substrate preparation	Substrate shall be dry, strong, crack-free, dimensionally stable and free from adhesion-impairing substances (e.g. dust, oil, wax, release agent, efflorescence, laitance, paint, lacquer and varnish residue). Fill any existing cracks in screed with Sopro GH 564 casting resin. Calcium sulphate (anhydrite) screeds shall exhibit a moisture content $\leq 0.5\% \text{ CM}$ (for heated screeds $\leq 0.3\% \text{ CM}$) to DIN 18 157 and be adequately ground and vacuum-cleaned. Cement screeds shall be 28 days old and dry ($\leq 2.0\% \text{ CM}$). Prior to flooring installation, screeds incorporating heating elements shall be heated up to ensure adequate drying or heated up and allowed to cool in accordance with relevant procedures and standards. Gypsum plasterwork shall be dry, single-coat and shall not be felt-floated or smoothed. Thin surface filler coats shall be removed. All relevant standards, guidelines and recommendations shall apply; workmanship shall comply with good practice.
Application	Stir or shake prior to use and apply by paint brush, block brush or roller. Apply material moderately so as to avoid puddling and skinning. Work may resume immediately after priming coat has fully dried through.
Application temperature	From +5 °C to max. +25 °C
Disposal	Properly emptied and cleaned containers may be handed over for recycling.
Note	Use Sopro MGR 637 multi-purpose primer or Sopro EPG 1522 epoxy primer where tiles of size $> 1.0 \text{ m}^2$ are to be laid on calcium sulphate-based substrates. Sopro EPG 1522 shall always be used for magnesium oxychloride (magnesite) screeds. For application of Sopro SG 602 to terrazzo, sand down terrazzo and ensure it is free from waxes and other adhesion-impairing substances. In relation to timber substrates, do not use Sopro SG 602 on woodstained and untreated wood or on timber floorboards. For large-format tiles (e.g. $> 0.36 \text{ m}^2$ tile size), we recommend a fast setting and fast drying Sopro tile adhesive in combination with Sopro SG 602.
Overcoatable	After 2 – 5 hours, depending on substrate suction, indoor environmental conditions and application temperature. Sopro SG 602 should in any case be left to dry for no longer than 24 hours.
Shelf life	Approx. 12 months, subject to cool storage in well sealed containers; protect from frost
Specified times	Apply for normal temperature range of +23 °C and 50 % relative humidity; higher temperatures shorten and lower temperatures lengthen these times.
Suitable substrates	Absorbent substrates such as cement render, lime/cement render, gypsum plaster, homogeneous, flush-jointed masonry (no composite masonry), concrete, aerated concrete, paperless gypsum panels, gypsum plasterboard and gypsum fibreboard, cement screeds, calcium sulphate screeds, natural stone, cast stone and terrazzo. For ceramic tiles and natural stone. Only use on timber substrates that are insensitive to moisture. Do not use on substrates exposed to risk of rising damp. For priming prior to tile-on-tile laying

dilutability	Dilute 1 : 1 with water on cementitious and calcium sulphate-based substrates. Apply in undiluted form to non-absorbent substrates (e.g. for priming prior to tile-on-tile laying).
tool cleaning	Wash tools with water immediately after use
tools	Lambswool roller, foam roller, paint brush, block brush
Licence	EMICODE system of GEV (German Association for the Control of Emissions in Products for Flooring Installation, Adhesives and Building Materials): EC1 ^{PLUS} ("very-low-emission-plus") rating
Safety precautions	<p>EUH208 Contains 1,2-Benzisothiazol-3(2H)-on. May produce an allergic reaction.</p> <p>EUH210 Safety data sheet available on request EUH208 Contains a mixture of: 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one in proportions 3 : 1. May produce an allergic reaction.</p> <p>P102 Keep out of reach of children.</p> <p>German Water Hazard Class (WGK) 1 (slightly hazardous to water)</p>
Disposal Considerations	<p>The generation of waste should be avoided or minimized wherever possible. Recover if possible. A waste code (EWC) according to European List of Waste (LoW) cannot be specified, due to dependence on the usage. Contact and send to an authorized waste disposal service.</p> <p>Methods of disposal:</p> <p>Disposal of this product, solutions, packaging and any by-products should at all times comply with the requirements of environmental protection and waste disposal legislation and any regional local authority requirements.</p> <p>Dispose of surplus and nonrecyclable products via a licensed waste disposal contractor.</p> <p>Do not dispose of waste into sewers.</p> <p>Clean waste packaging should be recycled when possible and authorized by the authority.</p> <p>Hazardous waste: No</p> <p>Disposal considerations:</p> <p>Do not allow to enter drains or watercourses.</p> <p>Dispose of product according to all federal, state and local applicable regulations.</p> <p>If this product is mixed with other wastes, the original waste product code may no longer apply and the appropriate code should be assigned.</p> <p>Dispose of containers contaminated by the product in accordance with local or national legal provisions. For further information, contact your local waste authority.</p> <p>Special precautions:</p> <p>This material and its container must be disposed of in a safe way. Care should be taken when handling untreated empty containers.</p> <p>Avoid dispersal of spilled material and runoff and contact with soil, waterways, drains and sewers.</p> <p>Empty containers or liners may retain some product residues. Do not re-use empty containers.</p>

bringing european innovation



FOR MORE INFORMATION CONTACT: **Smet Building Products Ltd**

93A Belfast Road | Newry | BT34 1QH | Northern Ireland

T: +44 (0)28 3026 6833 ROI: +353 (0) 1697 8586

E: info@smetbuildingproducts.com

smetbuildingproducts.com or smet.ie



The information, and, in particular, the recommendations relating to the application and end-use of SMET distributed products, are given in good faith based on SMET's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with the manufacturer's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. The manufacturer reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.